



Window Tint

Product	Color	Thickness	VLT	VLT Tolerance	UV Rejection	Glare Reduction	Infrared Rejection	Total Solar Energy Rejected
Jet Black								
Jet Black 5	Black	1.5 mils	5%	+/- 2%	99%	95%	13%	42%
Jet Black 15	Black	1.5 mils	16%	+/- 3%	99%	82%	13%	41%
Jet Black 20	Black	1.5 mils	20%	+/- 3%	99%	78%	13%	40%
Jet Black 30	Black	1.5 mils	32%	+/- 3%	99%	65%	13%	37%
Jet Black 35	Black	1.5 mils	35%	+/- 3%	99%	62%	13%	37%
Jet Black 43	Black	1.5 mils	43%	+/- 3.1%	99%	53%	13%	33%
Jet Black 50	Black	1.5 mils	50%	+/- 3%	99%	45%	13%	30%
Jet Black 55	Black	1.5 mils	55%	+/- 3%	99%	40%	13%	29%
Jet Black 70	Black	1.5 mils	70%	+/- 3%	99%	23%	13%	24%
Hybrid Ore								
Hybrid Ore 5	Black	1.5 mils	4%	+/- 1.5%	99%	96%	42%	60%
Hybrid Ore 20	Black	1.5 mils	25%	+/- 3%	99%	73%	42%	52%
Hybrid Ore 35	Black	1.5 mils	36%	+/- 3%	99%	60%	32%	48%
Hybrid Ore 50	Black	1.5 mils	54%	+/- 3%	99%	41%	32%	36%
Ceramic+								
Ceramic+ 5	Black	1.5 mils	6%	+/- 1.5%	99%	93%	96%	70%
Ceramic+ 15	Black	1.5 mils	14%	+/- 2.5%	99%	85%	96%	67%
Ceramic+ 30	Black	1.5 mils	30%	+/- 3%	99%	67%	96%	62%
Ceramic+ 50	Black	1.5 mils	49%	+/- 3%	99%	46%	96%	57%

Infrared Rejection as measured at 1,025 nm. All values are as applied to 1/8" (3mm) clear glass. The performance data reported was tested using ASHRAE, ASTM, BSEN 410, and AIMCAL Standards.