

BELBIEN ABRASION RESISTANCE TEST

Belbien is tested using the Taber Abrader or its equivalent. After 5,000 minimum revolutions of the Taber wheel, there is no appreciable change using a load of 1,000 grams or 2.2 lbs. weight. An S-11 refacing disk is used for troweling the abrasive wheels.

belbien



IDS INTERIOR DESIGN SOLUTIONS